



Prüfbericht - Nr.: Test Report No.:		IND/BLR/CH/2021/2295R		Seite 1 von 2 Page 1 of 2	
Auftraggeber: Client:		ENRICH ENCAP PRIVATE LIMITED SURVEY NO. 116/1/1/1, RUDANA VILLAGE, KHANVEL, 396230, INDIA			
Gegenstand der Prüfung: Test item:		ENCAP - F0298P			
Bezeichnung: Identification:		-		Serien-Nr.: Serial No./Document Submitted: Email Dated: 10.03.2021	
Wareneingangs-Nr.: Receipt No.:		12032021		Eingangsdatum: Date of receipt: 12.03.2021	
Order No.:		166535375		Testing Period: 12.03.2021 to 19.03.2021	
Prüfört: Testing location:		TÜV Rheinland India Pvt Ltd, Plot No. 27/B, 2nd Cross Road, Electronics City, Phase 1, Bangalore - 560 100, Karnataka, India.			
Prüfgrundlage: Test specification:		Customer's Requirement : Adhesion to Backsheet			
Prüfergebnis: Test Result:		Refer Page No.: 2 to 2			
Prüflaboratorium/ Testing Laboratory:					
zusammengestellt/ compiled by:			kontrolliert/ checked by:		
31.03.2021		 Raghukumar B S Sr. Engineer – Polymer Section, Material Testing Laboratories, Industry Services		31.03.2021	
				 Ranabir Pal Sr. Manager – Polymer Section, Material Testing Laboratories, Industry Services	
Datum Date	Name Name	Unterschrift Signature	Datum Date	Name Name	Unterschrift Signature
Sonstiges/ Other Aspects: This is an amended test report and this report replaces the earlier report IND/BLR/CH/2021/2295 dated 22.03.2021. The report is amended to remove the type of failure column and to change the test item name & unit of result as per client request.					
Abkürzungen:		ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar		Abbreviations: ok / P = passed fail / F = failed n.a. / N = not applicable	
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.					
<i>This test report relates to the a. M. Test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. Test item submitted by client. Sampling not done by TUVRI. Decision rule applied at 95% confidence level of measurement uncertainty with coverage factor k=2 while stating the conformity'.</i>					


Prüfbericht - Nr.:
Test Report No.:

IND/BLR/CH/2021/2295R

Seite 2 von 2
Page 2 of 2

TEST RESULTS

Discipline: Mechanical
Product Group: Rubber and Rubber Products



Photograph of sample as in received condition

Test Name: Adhesion to Backsheet
Test Method: ASTM D1876
Pre-Conditioning: 23±1°C & 50±2% RH for 7 days
Test Condition: Test speed – 254 mm/min
Observation:

Specimen No.	T-Peel Strength (N/cm)
1	55.2
2	43.4
3	39.8
4	39.1
5	57.9
Average	47.1

---- End of Report ----