





<b>Prüfbericht - Nr.:</b> <i>Test Report No.:</i>	<b>IND/BLR/CH/2021/2293R</b>	<b>Seite 1 von 3</b> <i>Page 1 of 3</i>			
<b>ULR No.:</b>	<b>TC568821500002293F</b>				
<b>Auftraggeber:</b> <i>Client:</i>	<b>ENRICH ENCAP PRIVATE LIMITED</b> SURVEY NO. 116/1/1/1, RUDANA VILLAGE, KHANVEL, 396230, INDIA				
<b>Gegenstand der Prüfung:</b> <i>Test item:</i>	<b>ENCAP - F0298P</b>				
<b>Bezeichnung:</b> <i>Identification:</i>	-	<b>Serien-Nr.:</b> <i>Serial No./ Document Submitted:</i>	Email Dated: 10.03.2021		
<b>Wareneingangs-Nr.:</b> <i>Receipt No.:</i>	12032021	<b>Eingangsdatum:</b> <i>Date of receipt:</i>	12.03.2021		
<b>Order No.:</b>	166535375	<b>Testing Period:</b>	17.03.2021 to 17.03.2021		
<b>Prüfort:</b> <i>Testing location:</i>	TÜV Rheinland India Pvt Ltd, Plot No. 27/B, 2nd Cross Road, Electronics City, Phase 1, Bangalore - 560 100, Karnataka, India.				
<b>Prüfgrundlage:</b> <i>Test specification:</i>	Customer's Requirement : Tensile Test				
<b>Prüfergebnis:</b> <i>Test Result:</i>	Refer Page No.: 2 to 3				
<b>Prüflaboratorium/ Testing Laboratory:</b>					
<b>zusammengestellt/ compiled by:</b>		<b>kontrolliert/ checked by:</b>			
31.03.2021	 Raghukumar B S Sr. Engineer – Polymer Section, Material Testing Laboratories, Industry Services	31.03.2021	 Ranabir Pal Sr. Manager – Polymer Section, Material Testing Laboratories, Industry Services		
<b>Datum</b> <i>Date</i>	<b>Name</b> <i>Name</i>	<b>Unterschrift</b> <i>Signature</i>	<b>Datum</b> <i>Date</i>	<b>Name</b> <i>Name</i>	<b>Unterschrift</b> <i>Signature</i>
<b>Sonstiges/ Other Aspects:</b> This is an amended test report and this report replaces the earlier report IND/BLR/CH/2021/2293 dated 18.03.2021. The report is amended to change the test item name as per client request.					
<b>Abkürzungen:</b> ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar			<b>Abbreviations:</b> ok / P = passed fail / F = failed n.a. / N = not applicable		
<b>Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.</b> <i>This test report relates to the a. M. Test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. Test item submitted by client. Sampling not done by TUVRI. Decision rule applied at 95% confidence level of measurement uncertainty with coverage factor k=2 while stating the conformity'.</i>					


**Prüfbericht - Nr.:** IND/BLR/CH/2021/2293R  
**Test Report No.:**

**Seite 2 von 3**  
*Page 2 of 3*

**ULR No.:** TC568821500002293F

### TEST RESULTS

Discipline: Mechanical  
Product Group: Rubber and Rubber Products



**Photograph of sample as in received condition**

**Test Name:** Tensile Test  
**Test Method:** ASTM D412  
**Test Condition:** Specimen type: Die C  
Gauge length: 25 mm  
Test speed: 500 mm/min

**Observation:**

**Direction A**

Specimen No.	Tensile Strength (MPa)	Elongation @ Break (%)
1	22.7	642
2	24.8	631
3	23.5	638
<b>Average</b>	<b>23.7</b>	<b>637</b>





**Prüfbericht - Nr.:**  
*Test Report No.:*

**IND/BLR/CH/2021/2293R**

**Seite 3 von 3**  
*Page 3 of 3*


**ULR No.:**

**TC568821500002293F**


**Direction B**

Specimen No.	Tensile Strength (MPa)	Elongation @ Break (%)
1	23.4	626
2	26.1	620
3	24.8	638
<b>Average</b>	<b>24.8</b>	<b>628</b>

**Direction A**



**Direction B**



**Test Graphs**

---- End of Report ----